

# Epoxy Gloss Coat

# Epoxy Gloss Coat Hygienic

# Epoxy Matt Coat

# Epoxy Matt Coat Hygienic








Watco Epoxy Gloss Coat has been re-formulated to produce a 'Best in Class' water based epoxy resin. This tough, easy to use coating now dries faster to reduce downtime and lasts longer to save recoating costs. The rapid drying formula also allows the application of 2 coats in one day. Our unique blend of the best resins available provide an attractive, low maintenance, hard wearing floor finish which lasts and lasts.

Epoxy Matt Coat is also available where a matt finish may be desirable to reduce glare or help hide minor imperfections in a worn concrete floor.

Hygienic grades incorporate Silver Ion technology and are ideal for areas where cleanliness and hygiene are as important as a hard wearing finish. Although the product tests as 'low slip potential', if positive traction is required, please specify Watco Safety Coat. All grades have impressive test results for abrasion, scratch and impact resistance as well as for adhesion, hardness and flexibility. They are also breathable, chemical resistant, safe for food production areas and have a Class 1 fire rating. The range carries an A+ VOC emissions rating with a low level of VOC.

All tests have been undertaken to ISO standard where applicable and demonstrated this 'Best Ever Formulation' to be 40% harder wearing than previously.

### Colours/RAL Reference

 Light Grey 0007500	 Mid Grey 7036	 Dark Grey 7005	 Blue Grey 7000
 Black 9005	 Mid Blue 5015	 Dark Blue 5005	 Mid Green 6002
 Signal Red 3020	 Hazard Yellow 1021	 White 9010	
 Stone 7032	 Tile Red		



Samples are available on request. While great care is taken with the colour samples shown, no guarantee can be given that they represent exactly the colours offered.

### Areas of use:

- Warehouse
- Production Areas
- Workshops
- Showrooms
- Most heavily trafficked floors

### Features:

- Tough, hard wearing floor finish for heavy wear areas
- Apply to bare or previously painted surfaces
- Easy roll, low odour application
- Apply 2 coats in one day to reduce downtime
- New colour formulations to RAL shades
- Gloss, Matt or Hygienic versions available
- Class 1 fire rating
- Tested safe for use in food production areas
- New 15L super sized tin available in Epoxy Gloss Coat Original

## Need help? Speak to the experts

Our dedicated and professional team are here to help you get the best results for your project. They will talk you through the preparation and application stages when using **Epoxy Gloss Coat, Gloss Coat Hygienic, Epoxy Matt Coat, Epoxy Matt Coat Hygienic.**

Call our expert team on: **01483 418 418** (Weekdays 8:00am - 5:30pm. Saturday 9:00am - 12:00pm)



# Epoxy Gloss Coat

# Epoxy Gloss Coat Hygienic

# Epoxy Matt Coat

# Epoxy Matt Coat Hygienic

## 1 Surface Preparation

**Bare Concrete** – remove surface laitance, dust and any light dirt or grease deposits using Watco Etch & Clean. Watco Etch & Clean also etches smooth, bare concrete surfaces to provide a key. Flush with clean water and allow the surface to dry. For the removal of heavier deposits of oil and grease we recommend Watco Concroff. Again, flush with clean water and allow the surface to dry. If residual damp remains this is acceptable as Epoxy Gloss Coat is breathable.

**Powerfloated or very smooth surfaces** – Watco Powerfloat Primer should be used on very smooth or power floated surfaces.

**New Concrete** – new concrete should be left for four weeks to dry in the summer and six in the winter. The surface should then be prepared using Watco Etch & Clean and thoroughly rinsed away and left to dry prior to applying this coating.

**Painted surfaces** – abrade to remove loose paint. Check remaining paint is well bonded. Very smooth, glossy paint should be lightly abraded to provide a key. Watco Bio-D can be used to remove grease and oil from painted surfaces.

**Highly porous surfaces** – a primer may be required for high suction surfaces such as sand and cement screed.

Please contact us for advice.

## 2 Mixing

Remove the two inner tins from the tall outer tin. Stir the contents of each tin thoroughly and pour all of the contents into the outer tin (5L) or large bucket (15L). Scrape around the inside of the tins to remove any residue. Mix the components together thoroughly using a spatula or similar wide bladed tool (a piece of wooden batten is ideal). Continue mixing until an even colour and consistency are obtained. Do not mix more than one pack at a time. If a paint stirrer fitted to an electric drill is used, also use the spatula to blend in any unmixed material from the sides and bottom of the tin.

## 3 Application

Best results are obtained in warm (minimum 15°C), dry conditions with good ventilation. In very high temperatures (30°C and above), it is recommended that bare concrete is lightly dampened first with water. Apply with a medium pile roller, working well into the surface of the concrete. Do not exceed the maximum coverage of 30m<sup>2</sup> per 5 litre pack, per coat. The product will darken slightly as curing commences and it should not be over rolled. The second coat can be applied as soon as the first coat is dry (generally 4-6 hours) and should be applied within 5 days. If more than 5 days elapse, the first coat should be lightly abraded before the second coat is applied. Avoid washing the surface for 7 days.

## 4 Safety

Material Safety Data Sheets are available.

## 5 Ordering

Available direct from Watco UK Limited and through agents worldwide. All Watco products are sold subject to the Company's Standard Conditions of Sale. The Company and its representatives are often asked to comment on potential uses of Watco products which differ from those described in the Company's data sheets. Whilst in such cases the Company and its representatives will always try to offer helpful and constructive advice, the Company cannot be held responsible for the results of such uses unless they are specifically confirmed in writing by Watco.

# Epoxy Gloss Coat

# Epoxy Gloss Coat Hygienic

# Epoxy Matt Coat

# Epoxy Matt Coat Hygienic

## Specification

<b>Composition</b>	Water based epoxy resin.
<b>Number of Components</b>	1 x curing agent, 1 x resin.
<b>Finish</b>	Coloured, glossy, smooth.
<b>Primer Required</b>	See 'Surface Preparation on p.2'
<b>Number of Coats</b>	2
<b>Dry Film Thickness</b>	100 microns.
<b>Wet Film Thickness</b>	160 microns.
<b>Usage Interior/Exterior</b>	Interior. Can fade if used outside.
<b>Application Tools</b>	Medium pile roller. Cut in using brush.
<b>Minimum Application Temperature</b>	Air temperature 15°C Floor temperature 10°C
<b>Suitable For</b>	Concrete, wood, sand and cement and existing, well bonded paint. The moisture content of concrete should be less than 75% RH.
<b>Coverage</b>	5L 30m <sup>2</sup> per coat., 15L 90m <sup>2</sup> per coat
<b>Pot Life</b>	Up to 2 hours at 20°C.
<b>Mix Ratio (by weight)</b>	100 parts curing agent : 120 parts resin.
<b>Cleaning Tools</b>	Warm soapy water.
<b>Shelf Life</b>	24 months in unopened containers.
<b>Cleaning</b>	Normal industrial cleaners - Watco Bio-D is ideal. Do not steam clean.
<b>Storage</b>	Between 15°C - 25°C for at least 8 hours prior to use. Do not allow to freeze.
<b>Principle Limitations</b>	Unsuitable for bare metal.
Please contact us regarding applications not described here.	Most self-levelling compounds cannot be painted - please ask for details. Lighter colours (e.g. whites, yellows and light greens) may require multiple coats due to lower opacity.

## Curing Time

	Recoat Time	Touch Dry	Light Traffic	Heavy Traffic	Full Chemical Resistance
10°C	6 - 8 hours	4 hours	16 hours	48 hours	7 days
20°C	4 - 6 hours	2 hours	12 hours	24 hours	7 days
30°C	4 hours	1 hour	12 hours	24 hours	7 days


Light Traffic: Foot, trolley, pallet truck, occasional forklift    Heavy Traffic: Regular forklift, heavy footfall, parked vehicles.

# Epoxy Gloss Coat Epoxy Gloss Coat Hygienic Epoxy Matt Coat Epoxy Matt Coat Hygienic

## Test Results

<p><b>ABRASION RESISTANCE ISO 5470-1</b> 57mg</p>	<p><b>Abrasion Resistance ISO 5470-1</b> Taber test method expresses results in mg on a scale between 0mg (highest resistance) and 3000mg (lowest). A reading below 3000mg is a CE mark pass.</p>	<p>3000mg → 0mg Lowest → Highest</p>	<p><b>FLEX ISO 1519</b> 2mm</p>	<p><b>Flexibility ISO 1519</b> Flexibility is measured using a Mandral Flex Tester, 2mm is the most flexible, 36mm the least.</p>	<p>36mm → 2mm Lowest → Highest</p>
<p><b>IMPACT RESISTANCE ISO 6272</b> CLASS3</p>	<p><b>Impact Resistance ISO 6272</b> Impact is expressed as Newton metres. Greater than 4 Nm is a CE mark pass.</p>	<p>Class 1 &gt;4Nm Class 2 &gt;10Nm Class 3 &gt;20Nm</p>	<p><b>GLOSS VALUE</b> Gloss 99 Matt: 4</p>	<p><b>Gloss Value</b> Rating is a 'Gloss Unit' measured on an Optical Glossmeter. Fine texture produces a mid-gloss finish on most substrates.</p>	<p>Matt 0-10%, Low Sheen 10-25%, Eggshell 26-40%, Semi-Gloss 41-69%, Gloss 70-85%, High Gloss +85%</p>
<p><b>SCRATCH RESISTANCE ISO 4586-2</b> 7N</p>	<p><b>Scratch Resistance ISO 4586-2</b> Scratch resistance is measured using a Sclerometer and the resistance is measured in Newtons. 1N is the lowest resistance, 20N the highest.</p>	<p>1N → 20N Lowest → Highest</p>	<p><b>CHEMICAL RESISTANCE</b> GOOD</p>	<p><b>Chemical Resistance</b> Results shown are for tests with commonly used chemicals. Advice can be given for chemicals not listed here.</p>	<p>Petrol, diesel, fuel, methylated spirits, xylene, ammonia, white spirit, bleach, oil, anti-freeze, mineral hydraulic oil, caustic soda, detergents, sugar solutions. At 5%: citric acid.</p>
<p><b>REACTION TO FIRE BS EN 13501-1:2018</b> Bfl-S1</p>	<p><b>Reaction to Fire BS EN 13501 – 1:2018</b> Testing to Radiant Panel and Single-Flame tests yielded the best results possible for an organic coating: Bfl-S1</p>	<p>Bfl → Does not easily ignite S1 → No smoke detected  Classification report available upon request.</p>	<p><b>FOOD TAINT EN 17/3</b></p>	<p><b>Food Taint Test, Sensory Test Method (Also EN71/3 Non Toxic)</b></p>	<p>Safe for food production areas</p>
<p><b>ADHESION EN 1542</b> 4.1MPa/Nmm<sup>2</sup></p>	<p><b>Adhesion Test EN 1542</b> Adhesion is expressed in MegaPascals (MPa) or Newton millimetres squared (Nmm<sup>2</sup>). Greater than 2 MPa is a CE mark pass.</p>	<p>&gt;2MPa (Nmm<sup>2</sup>) = test pass</p>	<p><b>WATER PERMEABILITY EN 1062-3</b> W<sub>3</sub></p>	<p><b>Water Permeability EN 1062-3</b> To achieve a CE mark, the measurement must be less than 0.1 kg/m<sup>2</sup>(24 h)0.5</p>	<p>CE Marking Critical Value: &lt; 0.1kg/m<sup>2</sup>/(24 h)0.5 W<sub>1</sub> → W<sub>2</sub> → W<sub>3</sub> Lowest → Highest</p>
<p><b>HARDNESS</b> 9H</p>	<p><b>Wolff-Wilborn Hardness Test</b> Also known as the 'pencil test', a 9H reading is the measure of a hardest coating, HB is the softest.</p>	<p>HB → 9H Least Hard → Hardest</p>			

## Standard Compliance



**BREEAM COMPLIANT**  
(for refurbishment)




**VOC LEVEL**

30g/Litre  
LOW



**ISO 16000**

The 'Loi Grenelle' measurement of the effect of a product's VOC level within a building. A+ is the top safety rating.



**REACH COMPLIANT**